

Technical features							
Dry-pressed ceramic tiles. Quality specifications, according to control tests of EN 14411-ISO 13006 Appendix G group B1a UGL			Standard requirements		Test results		Reference standard
			N ≥ 15 cm				
			(%)	(mm)	MATTE SOFT	MATTE	
	Lenght and with: deviation of the average size for each tile from the work size	Squadrato ISO 13006	± 0,3%	± 1 mm	± 0,15%		ISO 10545-2
	Thickness: deviation of the average thickness of each tile form the work size thickness	Squadrato ISO 13006	± 5%	± 0,5 mm	± 5%		
	Straightness: maximum deviation to the corresponding work sizes	Squadrato ISO 13006	± 0,3%	± 0,8 mm	± 0,10%		
	Orthogonality: permissible deviation in relation to the corresponding manufacturing dimensions	Squadrato ISO 13006	± 0,3%	± 1,5 mm	± 0,20%		
	Flatness: center curvature, edge curvature, and warpage in relation to the corresponding manufacturing dimensions	Squadrato ISO 13006	± 0,4%	± 1,8 mm	0,20%		
	Surface quality	A minimum of 95% of the tiles are to be free from visible defects			Compliant		
	Water absorption, percent mass fraction	≤ 0,5%			Average value 0,08%		ISO 10545-3
	Breaking strength in N (thickness < 7.5 mm)	≥ 700			Average value 1350 N		ISO 10545-4
	Bending strength in N/mm ²	≥ 35			Average value 52 N/mm ²		
	Resistance to deep abrasion	≤ 175 mm ³			Average value 140 mm ³		ISO 10545-6
	Thermal shock resistance	Available testing method			Resistant		ISO 10545-9
	Resistance to staining	Available testing method			Class 5		ISO 10545-14
	Resistance to low concentrations of acids and alkali	See manufacturer's declaration			LB	LA	ISO 10545-13
	Resistance to high concentrations of acids and alkali	Available testing method			HB	HA	
	Resistance to household chemicals and swimming pool salts	Minimum class B			A		
	Frost resistance	Required			Resistant		ISO 10545-12
	Release of hazardous substances	Declared value for GL surfaces intended for countertop applications			Compliant		DM 1-2-2007 Reg. CE 1935-2004
	Shod ramp slipperiness	See manufacturer's declaration			R9 (6° < α ≤ 10°)	R10 (10° < α ≤ 19°)	DIN EN 16165 ANNEX B
	Barefoot ramp slipperiness	See manufacturer's declaration			-	Class B (18° ≤ α < 24°)	DIN EN 16165 ANNEX A

Technical features									
Dry-pressed ceramic tiles. Quality specifications, according to control tests of EN 14411-ISO 13006 Appendix G group B1a UGL			Standard requirements		Test results				Reference standard
			N ≥ 15 cm						
			(%)	(mm)	MATTE SOFT	MATTE	CANNETÉ	GRIP	
	Lenght and with: deviation of the average size for each tile from the work size	Squadrato ISO 13006	± 0,3%	± 1 mm	± 0,15%				ISO 10545-2
	Thickness: deviation of the average thickness of each tile form the work size thickness	Squadrato ISO 13006	± 5%	± 0,5 mm	± 5%				
	Straightness: maximum deviation to the corresponding work sizes	Squadrato ISO 13006	± 0,3%	± 0,8 mm	± 0,10%				
	Orthogonality: permissible deviation in relation to the corresponding manufacturing dimensions	Squadrato ISO 13006	± 0,3%	± 1,5 mm	± 0,20%				
	Flatness: center curvature, edge curvature, and warpage in relation to the corresponding manufacturing dimensions	Squadrato ISO 13006	± 0,4%	± 1,8 mm	0,35%				
	Surface quality	A minimum of 95% of the tiles are to be free from visible defects			Compliant				
	Water absorption, percent mass fraction	≤ 0,5%		Average value 0,08%				ISO 10545-3	
	Breaking strength in N (thickness < 7.5 mm)	≥ 1300		Average value 2200 N				ISO 10545-4	
	Bending strength in N/mm²	≥ 35		Average value 50 N/mm²					
	Resistance to deep abrasion	≤ 175 mm³		Average value 140 mm³				ISO 10545-6	
	Thermal shock resistance	Available testing method		Resistant				ISO 10545-9	
	Resistance to staining	Available testing method		Class 4				ISO 10545-14	
	Resistance to low concentrations of acids and alkali	See manufacturer's declaration		LB	LA			ISO 10545-13	
	Resistance to high concentrations of acids and alkali	Available testing method		HB	HA				
	Resistance to household chemicals and swimming pool salts	Minimum class B		A					
	Frost resistance	Required		Resistant				ISO 10545-12	
	Dynamic coefficient of friction	See manufacturer's declaration		≥ 0,42 wet				ANSI-A326.3	
		See manufacturer's declaration		-			> 0,40	METODO BCRA	
	Shod ramp slipperiness	See manufacturer's declaration		R9 (6° < α ≤ 10°)	R10 (10° < α ≤ 19°)		R11 (19° < α ≤ 27°)	DIN EN 16165 ANNEX B	
	Barefoot ramp slipperiness	See manufacturer's declaration		-	Class B (18° ≤ α < 24°)		-	DIN EN 16165 ANNEX A	
	Pendulum test slipperiness	See manufacturer's declaration		-			PTV > 36 (slider 96)	BS EN 16165 ANNEX C	

Technical features						
Dry-pressed ceramic tiles. Quality specifications, according to control tests of EN 14411-ISO 13006 Appendix G group B1a UGL			Standard requirements		Test results	Reference standard
			N ≥ 15 cm			
			(%)	(mm)	GRIP	
	Lenght and with: deviation of the average size for each tile from the work size	Squadrato ISO 13006	± 0,3%	± 1 mm	± 0,15%	ISO 10545-2
	Thickness: deviation of the average thickness of each tile form the work size thickness	Squadrato ISO 13006	± 5%	± 0,5 mm	± 5%	
	Straightness: maximum deviation to the corresponding work sizes	Squadrato ISO 13006	± 0,3%	± 0,8 mm	± 0,10%	
	Orthogonality: permissible deviation in relation to the corresponding manufacturing dimensions	Squadrato ISO 13006	± 0,3%	± 1,5 mm	± 0,20%	
	Flatness: center curvature, edge curvature, and warpage in relation to the corresponding manufacturing dimensions	Squadrato ISO 13006	± 0,4%	± 1,8 mm	0,35%	
	Surface quality	A minimum of 95% of the tiles are to be free from visible defects			Compliant	
	Water absorption, percent mass fraction	≤ 0,5%			Average value 0,08%	ISO 10545-3
	Breaking strength in N (thickness < 7.5 mm)	≥ 1300			Compliant	ISO 10545-4
	Bending strength in N/mm ²	≥ 35			Average value 52 N/mm ²	
	Resistance to deep abrasion	≤ 175 mm ³			Average value 140 N/mm ³	ISO 10545-6
	Thermal shock resistance	Available testing method			Resistant	ISO 10545-9
	Resistance to staining	Available testing method			Class 4	ISO 10545-14
	Resistance to low concentrations of acids and alkali	See manufacturer's declaration			LA	ISO 10545-13
	Resistance to high concentrations of acids and alkali	Available testing method			HA	
	Resistance to household chemicals and swimming pool salts	Minimum class B			A	
	Frost resistance	Required			Resistant	ISO 10545-12
	Dynamic coefficient of friction	See manufacturer's declaration			≥ 0,42 wet	ANSI-A326.3
		See manufacturer's declaration			> 0,40	METODO BCRA
	Shod ramp slipperiness	See manufacturer's declaration			R11 (19° < α ≤ 27°)	DIN EN 16165 ANNEX B
	Barefoot ramp slipperiness	See manufacturer's declaration			Class C (α > 24°)	DIN EN 16165 ANNEX A
	Pendulum test slipperiness	See manufacturer's declaration			PTV > 36 (slider 96)	BS EN 16165 ANNEX C